

Micromax™ 4817N

Electronic Inks and Pastes

Conductive Silver Compositions For General Purpose Air-Dry Applications

The compositions described in this bulletin are suspensions of specially prepared silver powders combined with a variety of organic binder systems. They are air-dry or low temperature-curing formulations for application on substrates which will not generally tolerate high-temperature firing. They are formulated to produce electrically conductive paths on paper, plastic, rubber, cloth, wood, etc., and may be applied by dip, spray, brush, stylus, syringe or screen print.

These highly conductive air dry compositions exhibit versatility and are useful over a broad range of applications. Suggested uses are:

- Printed Electronics
- Tantalum Capacitors
- Static Shielding
- Electrical Games and Toys
- Microwave Applications
- PC Board Repair
- Electroplating Base

Drying rate is a function of the solvent system in a composition and method of application is dictated by viscosity, a function of binder to solvent ratio.

Dry strength, flexibility, adhesion and temperature stability are functions of the binder system. No one binder system exhibits optimum capabilities of all functions. Lower metal contents are generally least expensive if cost is a primary consideration. Higher metal contents develop maximum conductivity and load carrying capabilities, and are more easily soldered.

Allgemeine Informationen

Lösungsmittel

Micromax™ 8459

Rheologische Eigenschaften

Viskosität

0.22 - 0.28^[1] Pa.s

[1]: Brookfield LVT, #2 spindle, 60 rpm

Application technique

Theoretische Abdeckung

120^[2] cm²/g

[2]: Dip/Spray, at 50µm wet film thickness

Elektrische Eigenschaften

Spezifischer Oberflächenwiderstand

≤100^[3] mOhm per square

[3]: Dip/Spray, at 25µm film thickness

Storage and stability

Haltbarkeit

3^[4] Monate

[4]: in unopened containers, from date of shipment, at room temperature

Micromax™ 4817N

Electronic Inks and Pastes

Verarbeitung

How to use

Design & compatibility

• Design

- Micromax™ 4817N conductive silver compositions exhibit a moderately fast drying rate, good adhesion to most substrates and high conductivity. They are used to produce electrically conductive patterns on surfaces of paper, film, plastic, rubber or wood as well as on conventional ceramic substrates. They are widely used in the manufacture of tantalum capacitors to metallize the anode, making it a good electrical contact.
- For dip, spray, brush or screen print application, Micromax™ 4817N compositions can be cured in 16-20 hours at room temperature (25 °C) or may be oven cured in 1 hour or less at 60-100 °C.
- Micromax™ 4817N, for spray or dip application, is widely used in electroforming, in electroplating, in static shielding, in magnetic tapes and in the manufacture of tantalum capacitors. Its low metal content places Micromax™ 4817N in a moderate price range attractive for many applications.

Processing

• Application methods

- Micromax™ conductive silver compositions are formulated for application by screen printing, spraying, dipping, brushing, banding or stylus. In most cases the compositions are produced to a consistency suitable for use as received and require only stirring to redisperse the solids.
- Recommended thinners for individual compositions may be added, with thorough blending, to replace solvent losses or to make slight adjustments for ease of application. Only the recommended thinner should be used. In handling and using organic solvents, the safety precautions recommended by the solvent supplier should be observed.

• Curing

- 1 hour at 60 °C

• Effect of curing temperatures

- In an air-dry system, the metal-binder film is formed when the solvent system is evaporated or "dried".
- While some compositions, if given sufficient time, will adequately dry or cure at room temperature, a more effective result is achieved in much less time through low temperature thermal exposure with a moderate time/temperature drying or curing. Optimum properties in air & dry and low-temperature-cure compositions are developed only after the compositions have been properly dried or cured. The drying or curing cycle for most

Micromax™ 4817N

Electronic Inks and Pastes

compositions in a function of time versus temperature up to the point of degradation of the organic system. In a system which will dry or cure in from 12 to 16 hours at room temperature (25°C) the same degree of drying or curing can be achieved in less than 2 hours at 60°C and in less than 1 hour at 100°C.

- Elevated temperature drying or curing of these compositions can be continuous, box oven or infrared. The heat should be applied from the bottom up to permit internal gases to escape before the top surface is completely dry. "Flash drying", a momentary exposure to excessively high temperatures, is likely to form a surface skin that traps internal gases, resulting in bubbles in the dried film.
- Failure to achieve rated conductivity indicates either that the applied composition is too thin with poor uniformity or that it has been incorrectly dried and/ or cured.

• Soldering

- Some Micromax™ air dried compositions are more commonly used as conductive cements in lead attachment, attachment of discrete components or in simple interconnections. For these applications, solderability is not important and is not generally recommended.

• Electroplating/electroforming

- The use of Micromax™ air dry conductive silver compositions as bases for electroplating and electroforming is wide-spread. Ease of application, broad curing ranges, high conductivity and dimensional stability mark Micromax™ 4929N, 4922N and 4817N compositions as leaders in the field.

• Coverage

- Coverage of silver compositions depends on metal content and thickness of application. Screen print compositions printed with a 165 or 200-mesh screen will generally result in a cured film 12-20µm (0.48-0.8mil) thick. Brush band, dip or spray application will normally result in film thickness of 13-18µm (0.5-0.7mil). Thinner films (increases coverage) can be applied by thinning the compositions with the recommended thinner; however, this will result in a cured film with a higher sheet resistivity. Thicker films can be achieved by brushing or spraying simply by applying more material.
- The coverage Micromax™ 4817N compositions are for typical cured thickness of 12-20µm (0.48-0.8mil) as outlined above.

Storage and shelf life

Micromax™ 4817N compositions (air-dry) should be stored at room temperature. Shelf life of material in unopened containers is three months from date of shipment.

Micromax™ 4817N

Electronic Inks and Pastes

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

Druckdatum: 2025-01-24

Seite: 4 von 4

Revision: 2024-09-06 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.