

ATEVA® 1075A

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	9 %	

Rheological properties

Temperature	190 °C	
Load	2.16 kg	
Melt Flow Index	8 g/10min	ASTM D 1238

Typical mechanical properties

Tensile Strength	15 MPa	ASTM D 638
Elongation at break	692 %	ASTM D 638
Flexural modulus	115 MPa	ASTM D 790
Shore A hardness	94	ASTM D 2240
Shore D hardness	46	ASTM D 2240

Thermal properties

Melting temperature	98 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	924 kg/m ³	
---------	-----------------------	--