

# ATEVA® 1608

ATEVA®

## Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	16.3 %	

## Rheological properties

Temperature	190 °C	
Load	2.16 kg	
Melt Flow Index	8.4 g/10min	ASTM D 1238

## Typical mechanical properties

Tensile Strength	15 MPa	ASTM D 638
Elongation at break	750 %	ASTM D 638
Shore A hardness	92	ASTM D 2240
Shore D hardness	36	ASTM D 2240

## Thermal properties

Melting temperature	90 °C	ASTM D 3418
---------------------	-------	-------------

## Physical/Other properties

Density	938 kg/m <sup>3</sup>	
---------	-----------------------	--