

# ATEVA® 1880A

ATEVA®

## Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	18 %	

## Rheological properties

Temperature	190 °C	
Load	2.16 kg	
Melt Flow Index	500 g/10min	ASTM D 1238

## Typical mechanical properties

Tensile Strength	4 MPa	ASTM D 638
Elongation at break	570 %	ASTM D 638
Flexural modulus	31 MPa	ASTM D 790
Shore A hardness	85	ASTM D 2240

## Thermal properties

Melting temperature	78 °C	ASTM D 3418
Ring and ball softening point	89 °C	ASTM E 28

## Physical/Other properties

Density	930 kg/m <sup>3</sup>	
---------	-----------------------	--