

## ATEVA® 2604AX

ATEVA®

Product information			
Resin Identification	(EVAC)		ISO 1043
Part Marking Code	>(EVAC)<		ISO 11469
Vinyl acetate content	25	%	
Rheological properties			
Temperature	190	°C	
Load	2.16	kg	
Melt Flow Index	4.5	g/10min	ASTM D 1238
Thermal properties			
Melting temperature	78	°C	ASTM D 3418
Physical/Other properties			
Density	948	kg/m³	
Film Properties			
Stress at yield, machine direction, 500 mm/min	3.6	MPa	ASTM D 882
Maximum stress, machine direction, 500 mm/min	11.1	MPa	ASTM D 882
Maximum strain, machine direction, 500 mm/min	280	%	ASTM D 882

Printed: 2024-12-22

Page: 1 of 1

Revised: 2024-01-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and rate design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication is accurate; however, we do not assume any liability of users root networked, the users to he weters a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to he materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that texis. We recommend that persons intending to rely on any recommend that users seek

© 2024 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.