

ATEVA® 4200AC

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	41 %	

Rheological properties

Temperature	190 °C	
Load	2.16 kg	
Melt Flow Index	80 g/10min	ASTM D 1238

Typical mechanical properties

Tensile modulus	2 MPa	ASTM D 638
Tensile Strength	2 MPa	ASTM D 638
Elongation at break	1500 %	ASTM D 638

Thermal properties

Melting temperature	45 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	962 kg/m ³	
---------	-----------------------	--