

ATEVA® 1081G

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	9 %	

Rheological properties

Melt Flow Index	1.1 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	17 MPa	ASTM D 638
Elongation at break	700 %	ASTM D 638
Flexural modulus	123 MPa	ASTM D 790
Shore A hardness	95	ASTM D 2240
Shore D hardness	43	ASTM D 2240

Thermal properties

Melting temperature	102 °C	ASTM D 3418
---------------------	--------	-------------

Physical/Other properties

Density	933 kg/m ³	
---------	-----------------------	--