

ATEVA® 1212AX

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	12 %	

Rheological properties

Melt Flow Index	0.35 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Thermal properties

Melting temperature	97 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	932 kg/m ³	
---------	-----------------------	--

Film Properties

Maximum stress, machine direction, 500 mm/min	29 MPa	ASTM D 882
Maximum stress, transverse, 500 mm/min	31 MPa	ASTM D 882
Maximum strain, machine direction, 500 mm/min	410 %	ASTM D 882
Maximum strain, transverse, 500 mm/min	510 %	ASTM D 882