

ATEVA® 1608

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	16.3 %	

Rheological properties

Melt Flow Index	8.4 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	15 MPa	ASTM D 638
Elongation at break	750 %	ASTM D 638
Shore A hardness	92	ASTM D 2240
Shore D hardness	36	ASTM D 2240

Thermal properties

Melting temperature	90 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	938 kg/m ³	
---------	-----------------------	--