

ATEVA® 1615

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	16 %	

Rheological properties

Melt Flow Index	15 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	12 MPa	ASTM D 638
Elongation at break	720 %	ASTM D 638
Shore D hardness	33	ASTM D 2240

Thermal properties

Melting temperature	90 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	937 kg/m ³	
---------	-----------------------	--

Film Properties

Gloss, 45°	33	ASTM D 2303
Haze	3	ASTM D 1003