

# ATEVA® 1943SB

ATEVA®

## Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	19 %	

## Rheological properties

Melt Flow Index	30 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

## Thermal properties

Melting temperature	87 °C	ASTM D 3418
---------------------	-------	-------------

## Physical/Other properties

Density	940 kg/m <sup>3</sup>	
---------	-----------------------	--

## Film Properties

Maximum stress, machine direction, 500 mm/min	15 MPa	ASTM D 882
Maximum stress, transverse, 500 mm/min	13 MPa	ASTM D 882
Maximum strain, machine direction, 500 mm/min	520 %	ASTM D 882
Maximum strain, transverse, 500 mm/min	610 %	ASTM D 882