

# ATEVA® 2604AX

ATEVA®

## Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	25 %	

## Rheological properties

Melt Flow Index	4.5 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

## Thermal properties

Melting temperature	78 °C	ASTM D 3418
---------------------	-------	-------------

## Physical/Other properties

Density	948 kg/m <sup>3</sup>	
---------	-----------------------	--

## Film Properties

Stress at yield, machine direction, 500 mm/min	3.6 MPa	ASTM D 882
Maximum stress, machine direction, 500 mm/min	11.1 MPa	ASTM D 882
Maximum strain, machine direction, 500 mm/min	280 %	ASTM D 882