

ATEVA® Z4003AC

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	40 %	

Rheological properties

Melt Flow Index	3 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile modulus	3 MPa	ASTM D 638
Tensile Strength	9 MPa	ASTM D 638
Elongation at break	>1150 %	ASTM D 638

Thermal properties

Melting temperature	55 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	962 kg/m ³	
---------	-----------------------	--