

# SANTOPRENE® 121-50E500

## SANTOPRENE®

A soft, black, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material has controlled rheology for robotic or specialty extrusion applications. This grade of Santoprene® TPV is shear-dependent and can be processed on conventional thermoplastics equipment for extrusion. It is polyolefin based and recyclable within the manufacturing stream.

### Key Features

- Designed for applications requiring good elastic recovery
- Designed for improved UV resistance
- Recommended for applications requiring superior part surface appearance

### Product information

Resin Identification	TPV	ISO 1043
Part Marking Code	>TPV<	ISO 11469

### Typical mechanical properties

Tensile stress at 100% elongation, perpendicular	1.7 MPa	ISO 527-1/-2 or ISO 37
Stress at break, perpendicular	4 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	450 %	ISO 527-1/-2 or ISO 37
Brittleness Temperature	-61 °C	ASTM D 746
Shore A hardness, 15s	56	ISO 48-4 / ISO 868
Compression set, 70 °C, 24h	23 %	ISO 815

### Physical/Other properties

Density	910 kg/m <sup>3</sup>	ISO 1183
---------	-----------------------	----------

### Additional information

Processing Notes

### Processing Notes

Desiccant drying for 3 hours at 80 °C (180 °F) is recommended. This grade of Santoprene® TPV has a wide temperature processing window from 190 to 230 °C (375 to 445 °F) and is incompatible with acetal and PVC.