

SANTOPRENE® 121-80

SANTOPRENE®

A soft, black, UV resistant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of applications. This grade of Santoprene® TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion, blow molding, thermoforming or vacuum forming. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component
- Recommended for applications requiring excellent flex fatigue resistance
- Excellent ozone resistance
- Designed for improved UV resistance

Product information

Resin Identification	TPV	ISO 1043
Part Marking Code	>TPV<	ISO 11469

Typical mechanical properties

Tensile stress at 100% elongation, perpendicular	4.6 MPa	ISO 527-1/-2 or ISO 37
Stress at break, perpendicular	11 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	560 %	ISO 527-1/-2 or ISO 37
Brittleness Temperature	-59 °C	ASTM D 746
Shore A hardness, 15s	85	ISO 48-4 / ISO 868
Compression set, 23 °C, 24h	25 %	ISO 815

Thermal properties

RTI, electrical, 1.5mm	90 °C	UL 746B
RTI, electrical, 3.0mm	90 °C	UL 746B
RTI, strength, 1.5mm	90 °C	UL 746B
RTI, strength, 3.0mm	95 °C	UL 746B

Specific Application Suitability

Continuous Upper Temperature Resistance, 1000h	135 °C	SAE J2236
Detergent resistance	f3	UL 749
Detergent resistance	f4	UL 2157
Outdoor suitability	f1	UL 746C

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
UL recognition	yes	UL 94
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	1 mm	IEC 60695-11-10
UL recognition	yes	UL 94
Hot Wire Ignition, 1.5mm	PLC 3 s	UL 746A
Hot Wire Ignition, 3mm	PLC 2 s	UL 746A

SANTOPRENE® 121-80

SANTOPRENE®

Electrical properties

Relative permittivity, 60Hz	2.6	IEC 62631-2-1
Arc Resistance Performance Level Category	PLC 6 class	UL 746B
Electric Strength, Short Time, 2mm	28 kV/mm	ASTM D 149
High Amperage Arc Ignition Category, 1.5 mm	PLC 0 class	UL 746A

Physical/Other properties

Density	970 kg/m ³	ISO 1183
---------	-----------------------	----------

Injection

Drying Temperature	82 °C
Drying Time, Dehumidified Dryer	3 h
Processing Moisture Content	≤0.08 %
Max. regrind level	20 %
Min. mould temperature	10 °C
Max. mould temperature	52 °C
Back pressure	0.517 MPa

Extrusion

Drying Temperature	82 °C
Drying Time, Dehumidified Dryer	3 h
Melt Temperature Range	202 °C

Additional information

Processing Notes

Processing Notes

Desiccant drying for 3 hours at 80 °C (180 °F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230 °C (350 to 450 °F) and is incompatible with acetal and PVC.